

# Product Information

## High Performance Lubricants

# MOLYKOTE® HP-300 Grease

## FEATURES

- Compatible with most rubber and plastics
- Excellent stability at high temperatures
- Superior resistance to chemicals and solvents
- Minimal deterioration due to oxidation, appropriate for long-term lubrication
- Low vapor pressure (base oil)

## COMPOSITION

- Perfluoro polyether
- Fluorinated polymer

**Fully fluorinated grease provides extraordinary performance under extreme conditions**

## APPLICATIONS

- MOLYKOTE HP-300 Grease can be used broadly under harsh conditions such as low or high temperatures, corrosive, solvent, liquefied natural gasses, high vacuum, etc.
- Clean room equipment and semiconductor manufacturing equipment where the volatilization of the lubricating material is undesirable.

## TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard*	Parameter	Unit	Value
	Appearance		White
JIS K 2220	Penetration (worked 60 times)	mm/10	280
	NLGI class		2
	Service temperature range	°C	-65 to 250
	Density	g/cm <sup>3</sup>	2.0
MIL-S-8660	Bleed (200°C 24 hours)	%	8.0
MIL-S-8660	Evaporation (200°C 24 hours)	%	0.2
MIL-S-8660	Evaporation (200°C 1000 hours)	%	1.0
ASTM D2596	Four ball weld load (1500rpm/1minute)	N	3330
ASTM D2266	Four ball wear scar (1200rpm, 392N, 1 hour)	mm	1.1
JIS K 2220	Low temperature torque test (-20°C)		
	Starting torque	Ncm	4.1
	Running torque	Ncm	1.8
JIS K 2220	Low temperature torque test (-40°C)		
	Starting torque	Ncm	11
	Running torque	Ncm	3.6
	Base oil vapor pressure 20°C	Pa	4x10 <sup>-10</sup>

\* JIS: Japanese Industrial Standard.

ASTM: American Society for Testing and Materials.

MIL: Military Specification and Standards.

## HOW TO USE

Clean points of application. As is usual with lubricating greases, apply or fill by means of a brush, spatula, or automatic lubrication device.

## HANDLING PRECAUTIONS

Although MOLYKOTE HP-300 Grease is highly chemically stable, at temperatures in excess of 250°C the material will gradually decompose and release toxic gasses; be sure to have adequate ventilation if you expect the material to decompose. Do not smoke cigarettes that are contaminated with this product. Be sure to wash hands thoroughly after use.

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at [www.molykote.com](http://www.molykote.com). You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

## USABLE LIFE AND STORAGE

When stored, unopened in a cool, dark place this product, has a usable life of 36 months from the date of production.

## PACKAGING

This product is available in 100g and 500g plastic cans.

## LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, [www.dowcorning.com](http://www.dowcorning.com) or consult your local Dow Corning representative.

## LIMITED WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

## DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

## DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

## Website Guide

For more information on our company and how to contact us, visit our website, [www.molykote.com](http://www.molykote.com)

*We help you invent the future.™*

## VERTRIEB

**SAS Industriehandel**  
Heike Engelbrecht

Meinsdorfer Straße 48  
DE 06862 Dessau-Roßlau

Tel.: +49 34901 5120  
Fax: +49 34901 51211  
[engelbrecht@sas-industrie.de](mailto:engelbrecht@sas-industrie.de)